

FloArm Top SL1-ST

(Formerly known as MYK INDUFLOOR SL 1(ST))

Solvent free, Epoxy resin-based Self –Leveling interior floor topping with a thickness of 1.0mm



TECHNICAL DATA SHEET

Product Description

FloArm Top SL1-ST is a 100 % solid containing free flowing, four component solvent free system in preweighed packing for on-site mixing. The finished floor provides a hard wearing, smooth, glossy, joint free, impervious and easy to clean treated surface. Additionally, it has mild chemical and alkali resistance.

General

FloArm Top SL1-ST is a blend of epoxy resin system available in various colors. It is designed for use in a wide range of industrial environments where durable, joint free, low maintenance flooring is required.

Uses

- Engineering industries & Auto industries
- Clean rooms, Laboratories & Hospitals
- Electronic Handling & Manufacturing unit.
- Pharmaceutical –Bulk and Formulation.
- Computer assembly units
- IT and other Commercial Buildings

Features and Benefits

- Durable: Provides a hard, impact and abrasion resistant floor topping for interior floors.
- Chemical resistant: good resistant to wide range of chemicals
- Hygienic: Hygienic seamless floor which is easy to clean
- Attractive: available in wide range of colors
- Quick and Easy to apply
- Decreased Friction and static charge formation
- Does not support growth of bacteria and fungus
- Impervious

Application Method

Application:

The material once mixed should be used within its specified pot life; the material is poured on to the primed surface and spread evenly to the required thickness with a 2mm 'V' notched steel trowel. Care should be taken not to over work the resin. After spreading, the wet epoxy should be firmly rolled with a spiked nylon roller to help release any entrapped air in the material and assist leveling and removing any tool marks. The rolling should be carried out using a 'back and forth' technique along the same path. An overlap of 50% with adjacent paths is recommended.

Surface Preparation:

The concrete substrate must be sound and of sufficient compressive strength (minimum 20 N/mm²) with a minimum pull off strength of 1.5 N/mm² for a durable and lasting flooring. The substrate must be level, clean, dry and free of all contaminants such as dirt, oil, grease etc. All previous floor coating if any must be mechanically removed to the maximum extent possible. It is acceptable to re-lay on floor coating that has a firm bond (pull out strength of 1.5 N/mm²).

Concrete substrates must be prepared mechanically using abrasive blast cleaning, scarifying or grinding equipment to remove cement laitance and achieve an open textured surface. Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed. Repairs to the substrate, filling of blowholes/voids and surface leveling must be carried out using appropriate repair product. The concrete or screed substrate has to be primed or leveled in order to achieve an even surface. High spots must be removed by e.g. grinding. All dust, loose and friable material must be completely removed from all surfaces before application of the product,

FloArm Top SL1-ST

(Formerly known as MYK INDUFLOOR SL 1(ST))

Solvent free, Epoxy resin-based Self –Leveling interior floor topping with a thickness of 1.0mm

Preferably by brush and/or vacuum. Ensure moisture content of the concrete surface is below 4 % - no rising moisture according to ASTM D 4263 (Polyethylene sheet) and above dew point.

New Concrete:

Normal priming is limited to application below 4% surface moisture in concrete. If the moisture content is more, special primers for damp moist floors have to be applied. MYK arment special primers FloArm Primer 1250 or moisture barrier such as the Cempo® series of products are recommended. Consult the Technical Services team of MYK arment for product specification or guidance

Priming:

The concrete surface after proper and thorough surface preparation has to be primed with FloArm Primer 1260 or 1290. The primer is a solvent free resin system. It is designed for better adhesion with the substrate and the flooring system. The primer should be mixed in the given proportions supplied. The entire contents of the hardener should be poured into the base and should be mixed using a low speed drill machine with an attachment for about 3 minutes @ (150-200 RPM) to get a homogeneous mix. Once mixed, the primer should be applied immediately on to the prepared concrete surface. After priming, the surface has to be kept for drying - approximately 8-12 hrs. Depending on the ambient temperature before proceed to lay FloArm Top SL1-ST

Mixing:

The pre-weighed packs of the components - resin, hardener, filler and pigment has to be mixed for 3 to 4 minutes using a low speed electric stirrer (300 -400 rpm) with a spiral shaped stirrer. The components should be mixed in a suitably sized mixing vessel. The pigment should be added to the base and should be stirred for 30 seconds till proper dispersion of pigment paste in base. The hardener is then added to the base for about 3 to 4 minutes slowly until an even color, texture is obtained. Add the filler slowly into the mixing container, ensure stirring while pouring.

Important: Do not dump the powder component all at once. Mix till the material is completely homogeneous. Mix only that much quantity that could be finished in the stipulated pot life. We are not recommending part mixing, unless under expert supervision.

Note:

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile,



TECHNICAL DATA SHEET

Variations in level and wastage etc. . It is always recommended to do a field trial prior to large scale application.

Ideal application temperature should be between 23°C to 30°C. Other than this temp. Please consult MYK Arment.

Technical Data

Pot Life: @ 30° C approx. 15 Minutes
@ 20° C approx. 45 Minutes

Compressive strength: > 60N/mm² @ 3° C
(After 14 day) (IS 9162)

Abrasion Resistance: 0.35 mm loss as per IS 1237

Flexural Strength: >35 N/mm² @ 30 °C
(After 14 day) (IS 9162)

Tensile Strength: >16 N/mm² @ 30 °C
(After 14 day) (IS 9162)

Foot Traffic (ASTM C 722): 24 hours @ 30 °C,
48 Hours @25 °C

Vehicular traffic: 72 Hrs. at 30° C (ASTM C 722)

Chemical Resistance: 7 Days @ 30°C
(ASTM C 722 spot)

Full Cure: 7 days @ 30 °C (ASTM C 722)

Mixed Density: Approx. 1.65 Gm/cc

Shore D hardness: 70 - 80 @ 7 Days at 30° C

as per (ASTM D 2240)

FloArm Top SL1-ST

(Formerly known as MYK INDUFLOOR SL 1(ST))

Solvent free, Epoxy resin-based Self –Leveling interior floor topping with a thickness of 1.0mm



TECHNICAL DATA SHEET

Following values observed in laboratory cleaned surface condition and Humidity @ 50%, Temp 30		
1	Gloss at 60 Deg, 1 Day, as per ASTM D 2457	85
2	SKID Resistance on A Clean dry surface As per ASTM E303	50

Consumption

17 M² @ 1mm thickness for a pack of 28.5 kgs

Packaging

28.5 kgs composite packs

Storage and Shelf Life

1 year if stored in cool dry place under shaded area, away from any extreme temperature or direct sunlight.

Health & Safety

FloArm Top SL1-ST should be applied with gloves and care should be taken to see that it does not fall on skin or eyes. Splashes on to eyes have to be immediately washed with plenty of clean water and medical advice has to be taken

Product Categories Available



Legal Note

The information, and, in particular, the recommendations relating to the application and end-use of MYK Arment products, are given in good faith based on MYK Arment current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with MYK Arment's recommendations. In practice, the difference in materials, substrates and actual site conditions are such that no warranty in respect of merchant ability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application & purpose. MYK Arment reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request.