



Conplast® NC

Chloride free accelerating, water reducing admixture

Uses

To accelerate the setting and early strength gain of Portland cement concrete and mortar mixes without the introduction of chloride. Acts as a plasticiser, so gives significant increases in both ultimate and early strengths. Typical applications include precast concrete, concrete placed in cold weather, concrete for repairs, mortars for brickwork.

Advantages

- Chloride free, safe in prestressed and reinforced concrete
- Produces exceptionally high early strengths
- Plasticising action gives increased workability and / or increased strengths
- Early setting improves frost resistance
- Suitable for bricklaying mortar mixes
- Particularly effective in concrete at low temperatures

Description

Conplast NC is guaranteed completely free of all forms of chloride and is supplied as a light straw coloured liquid.

The main active ingredient is an inorganic formate

Standard compliance

Conplast NC complies with BS 5075 Part 1 and ASTM C494 Type C.

Properties

Specific gravity : 1.260 - 1.270 at 27°C

Freezing point : -16°C

Chloride content : Nil to BS 5075

Air entrainment : Less than 1%

Compatibility with cements : May be used with all types of Portland cements. Not suitable for use with high alumina cement

Acceleration : The addition of Conplast NC to Portland cement concrete mixes accelerates both the setting and rate of strength gain. The strength improvements are most significant during the first 18 hours.

Long term effects : Accelerated corrosion testing of steel in concrete has shown that Conplast NC does not affect the protection of steel afforded by cement against corrosion even at four times the normal dose level.

Application instructions

Dosage

The recommended dosage range for standard concrete and mortar mixes with all grades of Portland cement is 2.0 to 3.0 litres per 100 kg cement (see table).

Over dosage

An overdose of double the recommended amount of Conplast NC will result in a slight increase in initial acceleration, but will not materially alter the ultimate strength or characteristics of the cured concrete or mortar.

Mixing

Conplast NC should be stirred before use.

Dispensing

The correct quantity of Conplast NC should be measured by means of a recommended dispenser.

The company's technical department should be consulted regarding suitable equipment and its installation.

Conplast NC should be added direct into the mixer. Best results are obtained when added at the same time as the mixing water.

Curing

Concure WB, curing membrane or alternative methods such as polythene, water spray or wet hessian should be used.

Cleaning

Spillages of Conplast NC can be removed with water.

Estimating

Packaging

Conplast NC is supplied in 5, 20 & 200 litre drums.

Storage

Minimum shelf life of 12 months in unopened containers under normal warehouse conditions.

Conplast® NC

Typical effect of Conplast NC on strength gain :

Curing Temperature	Conplast NC Dosage Litres/100kg	Initial set (BS 5075) hrs.	Final set (BS 5075) hrs.	Compressive strength(N/mm ²)					
				10hrs	18hrs	24hrs	3Days	7Days	28Days
5°C	NIL	14	19	-	-	1.5	5.5	17	32
	2.5	12	17	-	0.5	3.0	10	20	36
10°C	NIL	4	06	-	-	2.5	08	20	35
	2.5	3	4 ½	-	2.0	4.5	13	24	40
20°C	NIL	3	4	1.0	4.5	6.0	17	29	43
	2.5	2	3	3.5	9.0	11.0	24	36	48

Precautions

Health and Safety instructions

Conplast NC is toxic. Do not ingest. If ingested, give an emetic of common salt in water and seek immediate medical attention. Prolonged contact with skin should be avoided. Any splashes should be washed well with water. The use of rubber gloves and safety glasses is recommended. Any splashes on eyes should be flushed immediately with plenty of clean water and medical treatment sought.

Fire

Conplast NC is non flammable. But, should be stored away from combustible materials.

Additional information

Technical data and guidance can be provided on a wide range of admixtures and concreting aids including plasticisers, retarders, air entraining agents, waterproofer, mould release agents, surface retarders, workability aids and repair materials.

Separate data sheets are available on those products.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

'Vishnu Chittam', No. 10, 2nd Floor
Sirur Park B Street, Seshadripuram
Bangalore 560020

www.fosroc.com

telephone

++91 80-2334 3188

fax

++91 80-2334 3178

e-mail

india@fosroc.com

Regional Offices

Bangalore

'Vishnu Chittam', No.10, 1stFloor
Sirur Park B Street, Seshadripuram
Bangalore 560 020
Ph:080-2334 3188
Fax : 080-23368667
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6411/12
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

109-113, 1st Floor, Vikrant Towers
4, Rajendra Place
New Delhi 110 008
Ph:011- 45062000-5
Fax: 011- 45062001
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799
- Ankleshwar : (02646) 220704/224687
- Bellary: 09845891690
- Bhubaneswar : (0674) 2521176
- Chennai : (044) 24899949/24853383
- Chandigarh : (0172) 2639360
- Cochin : (0484) 2347465
- Coimbatore : (0422) 2472966
- Goa : (0832) 09423058696
- Guwahati : (0361) 2462866
- Hyderabad : (040) 27662324/27662425
- Indore : (0731) 4049339
- Jaipur : (0141) 2336103
- Lucknow : (0522) 2239044
- Nagpur: (0712) 2753510/2563242
- Visakhapatnam : (0891) 2564850 / 2707607