Edition 01/01/2009 Identification no: 00 00 00 00 000 0 000000 Sika[®] Raingard

Sika® Raingard

Flexible, liquid applied, single component acrylic based ready to use waterproofing cum heat reflecting membrane system

7	
Product Description	Sika [®] Raingard is a flexible, liquid applied, single component, ultra violet rays and weather resistant, acrylic waterproofing membrane for all types of exposed roof slabs(new and old),terraces(sloped and flat),etc.It also helps to reflect heat from the surface thus producing a cooling effect. When combined with Sika [®] Fab 1 glass fibre mesh gives a highly durable waterproofing membrane system
Uses	Exposed roof waterproofing
	Impervious coating on roofs (flat and sloped) and concrete structures
	 As protective coating in infrastructure projects
	On non-trafficked areas
	Excellent adhesion to concrete, brickwork, corrugated asbestos, and asbestos cement sheet.
Characteristics /	■ Crack-bridging
Advantages	■ Flexible
	Water vapour permeable
	Simple application (even at detailing)
	Economical
	Bonds well to all types of masonry substrate
	 High diffusion resistance against CO₂
	Ultra violet rays and weather resistant
	 Algae and fungi resistant

Product Data

Technical Data

Form			
Appearance /Colours	Sika [®] Raingard: White liquid		
	(Can be stained with good quality stainer for light shades). Pre-test for over paintability and paint compatibility are recommended.		
Packaging	Sika® Raingard:10 kg Plastic Bucket		
	Sika [®] Raingard Primer- 2 kg HDPE Jerrycan		
Storage			
Storage Conditions/ Shelf-Life	Best before 6 months if stored properly in undamaged and unopened original sealed packaging in dry and cool conditions. Liquid component must be protected from frost.		



<u> </u>			
Chemical Base	Acrylic polymer dispersion Sika® Raingard:~1.400 kg/l at 27º C		
Density	Sika® Raingard Primer :~0.91 kg/l at 27º C		
Layer Thickness	With Sika [®] Fab-1 ~1.2 mm		
Service Temperature	+5 °C to +45°C		
Mechanical / Physical Properties			
Bond Strength	1.5 N/mm ² (According to ISO 4624)		
Crack bridging properties	2 mm (According to ASTM C 1305 - 06)		
Moisture permeability	Passes (According to IS101)		
Crack resistance	Passes 3 mm mandrel (According to IS101)		
Salt spray resistance	Satisfactory		
Workable time	15 minutes at +27º C		
Tack free time	25 minutes at +27º C		
Water permeability	Passes (According to IS 2645)		
Accelerated weathering, 500 hours	No cracking / no blister (According to IS 101)		
Solid Content	69 %		
Polymer Content	36%		
System Information			
System Structure	Layer thickness: 1.2 mm Primer: 1 x Sika® Raingard Primer First Coat: 1 x Sika® Raingard Fabric reinforcement : 1 x Sika® Fab 1 Second Coat: 1x Sika® Raingard Top Coat: 1x Sika® Raingard		
Application Details	Top odal. Thaingaid		
Consumption / Dosage	Sika® Raingard Primer: 0.200 kg/m² per coat depending on the substrate		
	Sika® Raingard: 0.5 kg /m² per coat (3 coats recommended)		
	Total thickness – 1.2 mm approx with Sika [®] Fab1 and 1mm without Sika [®] Fab1		
Substrate Quality	The cementitious substrate should be sound and of sufficient strength (min. 25 N/mm²). Minimum pull-off strength 1.5 N/mm², it should be free from grease, oil and contamination.		
Substrate Preparation	All dust, loose and friable materials and glaze or varnish of tiles must be completely removed by mechanical means. Existing coatings have to be inspected, cleaned and mechanically ground to achieve a sound, gripping substrate. In case of bad adhesion to the substrate, existing coatings have to be removed.		
	The uneven surface should be properly treated by suitable Sika® material to get a plain surface.		
Application Conditions / Limitations			
Substrate Temperature	+10 °C min / +40 °C max		
Ambient Temperature	+10 °C min / +40 °C max		
Application Instructions			
Priming	Prime the prepared substrate with Sika® Raingard Primer by brush or roller.		

2 Sika® Raingard

2/3

ŀ		

Application Method / Tools	Sika [®] Raingard is supplied in a single component pack and is in ready to use form. Stir thoroughly before application.			
	at of Sika [®] Raingard by brush or roller. Do it for application.			
	Place Sika® Fab1 over the first coat when it is in tacky condition			
	Apply the 2 nd and 3 rd coat of Sika [®] Raingard following the same above procedure at suitable time interval of 12 hours between the two coats			
Important Recommendation	The product can be stained with good quality stainer for light shades. However, pretest for consistency of colour shade is recommended through site trials before application.			
Cleaning of Tools	Clean all tools and application equipment with clean water immediately after use. Hardened / cured material can only be removed mechanically.			
Waiting Time /	Waiting time between coats			
Overcoating	+30°C	12 hours		
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.			
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.			
Legal Notes	that no warranty in respect of merchantal nor any liability arising out of any legal rel	n good faith based on Sika's current is when properly stored, handled and dance with Sika's recommendations. In strates and actual site conditions are such sility or of fitness for a particular purpose, ationship whatsoever, can be inferred written recommendations, or from any other ust test the product's suitability for the eserves the right to change the properties hird parties must be observed. All orders of sale and delivery. Users must always Product Data Sheet for the product		

concerned, copies of which will be supplied on request.



Sika India Pvt. Ltd. Commercial Complex II 620, Diamond Harbour Road Kolkata, 700 034, India Phone +91 33 2447 2448/2449 Telefax +91 33 2468 8688/2665 www.sika.in info@in.sika.com

3