

MAXTREAT[®] LAMINATE

High Performance, high strength, corrosion resistant pultruded Carbon fibre plates

Maxtreat Laminate is a composite fibre system where a carbon laminate strip is used in conjunction with an epoxy adhesive, Maxtreat Glue.

Uses

Maxtreat Laminate system is used for increasing load carrying capacity of structural members particularly where increase in live load / traffic loads is expected. It can also be used to repair when damage to structural member has occurred due to rebar corrosion, earthquake fire etc. and also in structural members having defects such as insufficient reinforcement and structural depth.

Benefits

- Very high strength to thickness or weight ratio - Appreciable increase in strength and load carrying capacity without significant increase in dead load.
- Enhanced stiffness, shear and tensile capacities - Increased load carrying capacity and better resistance to seismic forces and deflection.
- Chemical resistance- excellent resistance to acids and alkalis.
- Thin sections- can be effectively used in space constrained areas.
- Economical - easy to install, time and labour saving.

Properties

(Typical Values)- **Maxtreat Laminate**

TYPE	DIMENSIONS	TENSILE	ELASTICITY	ELONGATION
(standard)	Width x Thickness (mm)	STRENGTH (MPa)	MODULUS (GPa)	AT BREAK %
Maxtreat Laminate	50x1.4	2350	140	1.4
Maxtreat Laminate	100x1.4	2350	140	1.4

Laminates with higher modulus of elasticity can be supplied on request

Instruction for use

Surface Preparation

Concrete to be treated shall be free from oil residues, demoulding agents, curing compounds, grout holes and protrusions. The concrete surface to be glued with carbon strip shall be structurally repaired prior to treatment. Corrosion induced damages and structural damages shall be repaired by using epoxy grouting / appropriate mortars from Thermax range.

Mixing

The base and hardener of Maxtreat Glue shall be emptied into a suitable container and mixed with low speed, heavy duty drill fitted with a paddle and ensuring the sides are scrapped down. An uniform grey colour should be obtained after mixing thoroughly.

Application

The carbon strips shall be cut to the recommended sizes before hand due to the impossibility of joint by lapping. Mixed adhesive is applied using a rubber spatula /serrated trowel or other suitable spreader on to the roughened surface of the carbon strip such that the thickness of epoxy adhesive is around 4mm. The adhesive applied on the carbon strip is now adhered to the prepared substrate such that excess mixed adhesive squeezes out from both sides of the plate. the overflown excess material shall be removed using rubber spatula or by suitable means.

Maxtreat Glue

Compressive strength 40N/mm² at 1 day
>60N/mm² at 7 days

Shear strength 13 N/mm²

Pot life 30 min @ 40°C

Open time 60 min @ 40°C

Curing time 7 days

Adhesive bond strength > 10 N/mm²

Elastic modulus 4KN/mm²

Mixed Density 1.45-1.80 kg/litre

Vol. of solids 100%

MAXTREAT[®] LAMINATE

Curing

The adhesive will become tack free in approx. 4-6 hours and fully cured in 7 days.

Cleaning

Tools and equipment shall be cleaned with cleaning Sol solvent immediately after use. Hands and Skin shall be washed with soap, or an industrial hand cleaner.

thickness.

Health & Safety Instructions

Some people are sensitive to epoxy resin systems and may develop dermatitis on skin contact. Rubber gloves and/or barrier creams, protective clothings, goggles and respirator shall be worn on handling the materials. Sufficient mechanical and/or local exhaust ventilation shall be provided to maintain easy working conditions. If contact with skin or eyes occurs, washing with plenty of water is suggested. Solvent should not be used. If irritation persists, immediate medical advice shall be sought. Smoking is prohibited during application/handling of the product.

Storage

Maxtreat Glue : atleast 12 months if stored in dry conditions in unopened containers.

Maxtreat Laminate can be used upto 3 years.

Packing

Maxtreat laminate is supplied as rolls of length 50m.

Maxtreat Glue is supplied in 2 ltr packs.

Coverage


Maxtreat Glue will cover 1 lit/m² @ 1 mm thickness.

Other segments :

- Concrete Admixtures • Surface Treatments • Grouts & Anchors • Repair & Rehabilitation • Protective Coatings • Industrial Flooring • Waterproofing • Sealants • Adhesives • Cement Grinding Aids

Disclaimer: The information contained in this document is true and accurate to the best of our knowledge and is based on our experience & test results. It is always the Company's endeavor to give true and accurate information however as it does not have any direct and/or continuing control on the use of the Products , the Company cannot accept any liability , direct or indirect as a consequence of the use of Products. In the event of any doubt upon any critical parameter it is advisable to seek clarification from our technical representative.

We reserve the right to amend any product details without notice. Copyright© Thermax Limited Edition: (TCC/TDS/0915)



THERMAX

Thermax Limited
Environment House, Plot No.90-92
BG Block, MIDC, Bhosari,
Pune 411 026, India.
Tel: +91-20-67156152,
67156000
Fax: +91-20-27120206
Customer Care: 18002090115 (India toll
free) Email :
chemicals@thermaxindia.com

Ahmedabad

Tel: +91-79-26575408 • Fax: +91-79-65577270

Bengaluru

Tel: +91-80-22371721 • Fax: +91-80-22371726

Chennai

Tel: +91-44-24303400 • Fax: +91-44-24353841

Delhi

Tel: +91-11- 46087200 • Fax: +91-11- 26145311

Hyderabad

Tel: +91-40-23253700 • Fax: +91-40-23253799

Kolkata

Tel: +91-33-66070800 • Fax: +91-33-66070999

Mumbai

Tel: +91-22-67542222 • Fax: +91-22-22040859

Thermax World-wide

UK, USA, UAE, Germany, Belgium, Denmark, Russia,
Saudi Arabia, Thailand, Malaysia, Bangladesh,
Sri Lanka, China, Philippines, Peru, Chile, Kenya,
Nigeria, Brazil, Indonesia

Website: www.thermaxindia.com

Thermax Business Portfolio

Chemicals

Absorption Cooling

Air Pollution Control

Boilers & Heaters

Power

Water & Waste Solutions

Solar